

Method for flotation of iron ores, in which at conditioning of pulp the emulsion of straw oil in the solution of soap of tall oil is used as a flotator at ratio of soap of tall oil and straw oil equal to 2:1, which leads to increase of the effectiveness of the flotation process.