

A method of incrustation by amber includes cutting of seat of required configuration in wooden basis according to developed sketch, placing of amber in this seat and fashioning of common surface for all set. Before placing amber into seat amber is crushed to obtain grits having different dimension of granules, and after placing in seat amber grits are impregnated by liquid mixture on basis of epoxy resin to produce fluid phase and till hardening. Before placing grits in seat inclusions of other materials are introduced, said inclusions are previously processed to obtain required configuration, and are previously fixed on their places according to sketch. Bottom part of seat is covered by light-reflecting material. Amber grits and inclusions are located in such a manner that they stand out over basis surface.