

An antifriction composition contains phenol-formaldehyde resin, graphite and filling agent based on oilcoke. The composition contains solid phenol-formaldehyde resin with fluidity of not less than 8 cm and water content of not more than 2 weight % as phenol-formaldehyde resin.