

The invention relates to the field of electric arc indirect welding, namely to the compositions of fluxes, and it can be used in production of pipes, boilers of railroad tank cars in machine building and shipbuilding. A composition of ceramic flux for indirect welding on the flux backing contains silica, calcium oxide, alumina, fluorspar, magnesite, silicon, manganese, iron. Additionally ferromagnetic material is introduced into the composition of flux.