

Invention relates to the methods of producing the castings of complex configuration from aluminum alloys, mainly impellers of centrifugal compressors and can be used in power machine building and other branches of industry. Method includes heating the plaster mold obtained with the aid of a permanent pattern, to the temperature of 150-200 °C and its filling with metal melt.