

The invention relates to a skinnery branch of light industry and can be used in skinnery enterprises, making leathers for upper part of shoes.

The method comprises first pickling of offal by sodium chloride and acid, preliminary tannage on used pickled liquid by aluminum compound in the presence of sodium formate and syrup, with further increasing of alkalinity, shaving with washing. And also the second pickling, main tannage by potassium alum and ammonia alum, neutralizing, fat-liquoring and fixed treatment by aluminum compounds and sodium formate.