

The invention relates to leather industry and can be used for production of skins, mainly by method of chroming. A method of chrome-tanned leather drying consists in fanning with heat carrier through vapor permeable straps. Screen cloth of heat-resistant monofilaments with diameter of 0.1-0.3 mm and effective screening area of 0.48-1.0 is used as vapor permeable straps. Fanning is carried out in two stages, the temperature of heat carrier at the second stage is below than its temperature at the first stage by 10-30°C.