

The invention relates to steel metallurgy and perfects technology of converter production of steel at the upper bath lancing with oxygen with the use of low-manganese cast-iron. A method involves scrap charging, cast-iron pouring with manganese content of 0.05-0.50%, bath lancing with oxygen, removal of intermediate slag with the subsequent addition of lime and manganous material.