

Catalyst for dehydrogenation of ethyl benzene to styrene in the form of granule has porosity within the limits of 0.15-0.35 cm³/g. More than 50% of pores have a radius more than 600 Å and less than 1800 Å. Catalyst has not macro-pores with a radius exceeding 50000 Å.