

The invention relates to the fur production. A method includes soaking, fleshing, degreasing, pickling, tanning by sodium sulfatozirconilate and greasing. Before the tanning in a pickling liquid the sodium acetate is added, thus the expenditure sodium sulfatozirconilate is 2...6 g/l from computation on the zirconium (IV) oxide, and sodium acetate - 50...70 % from mass of sodium sulfatozirconilate.