

Raw mixture for production of Portland cement clinker for improving of rheologic properties and reduction of energy consumption for process of clinker production includes 22.0 - 30.0 per cent by weight of coal cleaning rejects of cake and by-product process, 4.0 - 5.0 per cent by weight of lignin, 2.5 - 3.0 per cent by weight of dehydrated deposition of municipal sewage works and carbonate component to reach 100 per cent by weight.