

The invention relates to a method for making pozzolans, synthetic blast-furnace slag, belite or alite clinkers, and pig-iron alloys, from oxidic slag, in which the oxidized liquid slag is reduced over an iron bath, with carbon being injected into the iron bath by means of bath tuyeres, in order to maintain a carbon content of between 2,5 % and 4,6 % by weight.