

A method of dyeing the natural fur includes preliminary neutralization and treatment of the fur with a temperature of 45°C during 2 h, the bath module is equal to 30 in solution of 40 % acetic acid and a dyer. A surface-active substance of anion type - sulfonal and benzyl spirit as intensificator are added to the dyeing bath.