

Process of receiving an electrode pitch by heat treatment of medium-temperature pitch at 340-360 °C together with an intensifying agent – the addition in the form of the polymerized melt from the by-products of chemical-recovery manufacture in composition of: polymers of benzene separation, anthracene fraction and mixture of sour resins. As a result receive an electrode pitch of the set quality with improved rheological properties is received.