

A method for making flax stock through holding flax straw in sealed chamber. Flax straw is wetted to 100 % humidity with 10 % water solution of melassa, with holding in sealed chamber with restricted air access at temperature of 30 °C for 5 days.