

A method for the production of bactericidal polymer monofilaments wherein one obtains polymer melt, adds admixture with formation of monofilaments and performs thermo-orientation spinning. As admixture one uses polyhexamethyleneguanidine chloride or polyhexamethyleneguanidine phosphate, at that admixture is added at the stage of formation.