

A method for removal inclusions of the second phase from crystals on the basis of CdTe includes heat treatment of a sample in cadmium vapor in vacuumized sealed quartz ampoule, at that the heat treatment is carried out at a sample temperature of 1100 K and cadmium vapor source temperature of 1070 K for 2 hours with subsequent programmed cooling with the rate of 5 K/min.